

Chromium On The Tie, Found In 969 Different Particles In 319 Configurations (50 Most Common)

Overall Rank	1st	2nd	3rd	4th	1st Avg Wt	2nd Avg Wt	3rd Avg Wt	4th Avg Wt	5th+ Avg Wt	Number
148	Fe	Cr	Ni	Si	72%	16%	9%	2%	1%	133
290	Fe	Cr	Ni	Mn	69%	16%	11%	2%	1%	66
407	Fe	Cr	Ni	Al	70%	16%	10%	3%	2%	46
416	Al	S	Ni	Cr	73%	12%	9%	3%	3%	44
713	Fe	Cr	Ni	S	71%	16%	11%	1%	1%	22
741	Fe	Cr	Ni	Ca	67%	17%	9%	3%	4%	21
742	Fe	Cr	Si	Ca	83%	12%	2%	1%	1%	21
864	Fe	Ni	Cr	Al	55%	22%	16%	5%	3%	17
905	Fe	Cr	Ca	Si	79%	13%	4%	2%	2%	16
957	Fe	Cr	Si		85%	14%	1%	0%	0%	15
1062	Fe	Cr	Ni	Cu	65%	16%	12%	5%	3%	13
1105	Cl	Na	Cr	Ni	69%	14%	7%	5%	5%	12
1183	Fe	Ni	Cr	Si	83%	10%	6%	1%	1%	11
1260	Cl	Na	Ni	Cr	68%	14%	6%	5%	6%	10
1366	Fe	Cr	Si	Ni	72%	16%	5%	4%	4%	9
1433	Al	Ni	S	Cr	71%	14%	11%	2%	2%	8
1459	Ca	S	Ni	Cr	53%	42%	3%	1%	0%	8
1486	Fe	Cr	Ni		71%	18%	11%	0%	0%	8
1490	Fe	Ni	Cr	Pd	46%	23%	19%	7%	6%	8
1622	Fe	Al	Cr	Si	90%	5%	2%	1%	2%	7
1627	Fe	Cr	Al	Si	85%	11%	2%	1%	0%	7
1629	Fe	Cu	Cr	Ni	54%	26%	10%	7%	3%	7
1776	Ca	S	Al	Cr	51%	37%	6%	2%	5%	6
1797	Cr	K	Pd	Fe	45%	38%	8%	5%	4%	6
1798	Cu	Fe	Ni	Cr	55%	27%	13%	3%	2%	6
1819	Fe	Cr	Ni	Zn	62%	16%	11%	4%	7%	6
1821	Fe	K	Ni	Cr	75%	10%	7%	4%	4%	6
1825	Fe	Ni	Cr	Cu	64%	17%	11%	6%	3%	6
1827	Fe	Ni	K	Cr	56%	20%	8%	6%	11%	6
2022	Ca	S	Si	Cr	54%	44%	2%	1%	0%	5
2067	Fe	Al	Ni	Cr	51%	18%	14%	10%	7%	5
2076	Fe	Cr	Al		90%	8%	2%	0%	0%	5
2077	Fe	Cr	Mn	Si	93%	5%	1%	1%	0%	5
2078	Fe	Cr	Ni	Ti	70%	14%	10%	4%	2%	5
2079	Fe	Cr	Si	Mg	81%	12%	4%	2%	1%	5
2080	Fe	Cr	Si	S	74%	12%	4%	3%	7%	5
2082	Fe	Cu	Ni	Cr	45%	31%	13%	7%	4%	5
2084	Fe	Ni	Cr	Ca	70%	13%	7%	3%	6%	5
2171	Si	Fe	Ni	Cr	72%	17%	7%	4%	0%	5
2388	Co	Cr	Ni	Fe	40%	20%	19%	16%	5%	4
2389	Cr	K	Pd		55%	38%	7%	0%	0%	4
2390	Cu	Ni	Fe	Cr	76%	14%	8%	1%	1%	4
2418	Fe	Cr	Mn	Ni	66%	14%	8%	6%	6%	4
2419	Fe	Cr	Ni	Pd	64%	16%	9%	7%	4%	4
2431	Fe	Ni	Cr	Mn	76%	13%	8%	2%	2%	4
2432	Fe	Ni	Cr	S	63%	17%	13%	4%	2%	4
2582	Sn	Ni	Cr	Si	94%	3%	2%	1%	0%	4
2726	Ca	Cr	Si		97%	2%	1%	0%	0%	3
2779	Ca	S	Cr		55%	45%	1%	0%	0%	3
2851	Co	Ni	Cr	Fe	41%	21%	20%	15%	4%	3