

Silver On The Tie, Found In 300 Different Particles In 173 Configurations (50 Most Common)

| Overall Rank | 1st | 2nd | 3rd | 4th | 1st Avg Wt | 2nd Avg Wt | 3rd Avg Wt | 4th Avg Wt | 5th+ Avg Wt | Number |
|--------------|-----|-----|-----|-----|------------|------------|------------|------------|-------------|--------|
| 814 | Ag | Cl | Ni | S | 90% | 5% | 2% | 1% | 2% | 18 |
| 1087 | Ag | Cl | Ni | Si | 91% | 5% | 2% | 1% | 1% | 12 |
| 1223 | Ag | S | Ni | Al | 86% | 11% | 3% | 1% | 0% | 10 |
| 1427 | Ag | Cl | Ni | Al | 88% | 8% | 2% | 2% | 1% | 8 |
| 1428 | Ag | S | Al | | 86% | 11% | 3% | 0% | 0% | 8 |
| 1566 | Ag | S | Cl | Al | 85% | 10% | 2% | 2% | 1% | 7 |
| 1714 | Ag | Cl | Ni | Ca | 89% | 6% | 2% | 1% | 1% | 6 |
| 1715 | Ag | Cl | S | Ni | 87% | 6% | 3% | 2% | 2% | 6 |
| 1716 | Ag | Ni | Cl | S | 91% | 4% | 2% | 1% | 1% | 6 |
| 1948 | Ag | Cl | Al | Ni | 74% | 14% | 8% | 3% | 2% | 5 |
| 1949 | Ag | S | Ni | Mg | 85% | 12% | 2% | 0% | 0% | 5 |
| 1950 | Ag | S | Pd | Cl | 80% | 9% | 6% | 4% | 1% | 5 |
| 2241 | Ag | S | Cl | | 88% | 9% | 2% | 0% | 0% | 4 |
| 2628 | Ag | Al | Cl | Ni | 57% | 20% | 13% | 3% | 7% | 3 |
| 2629 | Ag | Cl | Ca | Ni | 83% | 6% | 4% | 3% | 4% | 3 |
| 2630 | Ag | Cl | Pd | S | 72% | 15% | 8% | 2% | 3% | 3 |
| 2631 | Ag | Cl | Si | Ni | 89% | 3% | 2% | 2% | 4% | 3 |
| 2632 | Ag | Ni | Cl | Al | 90% | 3% | 2% | 2% | 3% | 3 |
| 2633 | Ag | S | Al | Ni | 79% | 11% | 5% | 3% | 3% | 3 |
| 2634 | Ag | S | Cl | Si | 84% | 11% | 3% | 1% | 0% | 3 |
| 2635 | Ag | S | Ni | | 84% | 12% | 4% | 0% | 0% | 3 |
| 2636 | Ag | S | Pd | Al | 76% | 11% | 7% | 4% | 2% | 3 |
| 2637 | Ag | S | | | 88% | 12% | 0% | 0% | 0% | 3 |
| 3258 | Ag | Al | Cl | Si | 72% | 13% | 9% | 2% | 4% | 2 |
| 3259 | Ag | Ca | Cl | Si | 64% | 15% | 8% | 6% | 7% | 2 |
| 3260 | Ag | Ca | S | Ni | 66% | 17% | 8% | 5% | 4% | 2 |
| 3261 | Ag | Cl | Ca | S | 62% | 16% | 8% | 6% | 9% | 2 |
| 3262 | Ag | Cl | Ni | | 88% | 9% | 3% | 0% | 0% | 2 |
| 3263 | Ag | Cl | Si | | 81% | 17% | 2% | 0% | 0% | 2 |
| 3264 | Ag | Fe | Cl | Al | 50% | 26% | 13% | 7% | 5% | 2 |
| 3265 | Ag | S | Al | Cl | 80% | 10% | 5% | 3% | 3% | 2 |
| 3266 | Ag | S | Al | Si | 81% | 13% | 2% | 2% | 2% | 2 |
| 3267 | Ag | S | Br | Si | 90% | 10% | 1% | 0% | 0% | 2 |
| 3268 | Ag | S | Br | | 88% | 11% | 1% | 0% | 0% | 2 |
| 3269 | Ag | S | Cu | Ni | 86% | 4% | 3% | 2% | 5% | 2 |
| 3270 | Ag | S | Ni | Ca | 76% | 11% | 3% | 2% | 7% | 2 |
| 3271 | Ag | S | Ni | Cl | 85% | 12% | 2% | 1% | 0% | 2 |
| 3272 | Ag | S | Si | Al | 76% | 9% | 6% | 4% | 5% | 2 |
| 3273 | Ag | S | Si | Mg | 81% | 9% | 5% | 3% | 3% | 2 |
| 3274 | Ag | Si | Al | Cl | 40% | 23% | 19% | 6% | 13% | 2 |
| 3746 | Fe | Ag | S | Ni | 61% | 29% | 5% | 3% | 3% | 2 |
| 3747 | Fe | Ag | Zn | Ni | 74% | 12% | 7% | 4% | 3% | 2 |
| 4413 | Zn | Ag | S | Ni | 58% | 21% | 7% | 6% | 8% | 2 |
| 4471 | Ag | Al | Ca | Si | 34% | 33% | 16% | 7% | 9% | 1 |
| 4472 | Ag | Al | Cl | Ca | 61% | 23% | 13% | 2% | 2% | 1 |
| 4473 | Ag | Al | Cl | Fe | 92% | 4% | 1% | 1% | 2% | 1 |
| 4474 | Ag | Al | Cu | Ni | 89% | 4% | 3% | 2% | 2% | 1 |
| 4475 | Ag | Al | S | Ni | 80% | 8% | 6% | 4% | 2% | 1 |
| 4476 | Ag | Al | S | Si | 65% | 11% | 9% | 6% | 9% | 1 |
| 4477 | Ag | Ba | Cl | S | 82% | 9% | 3% | 3% | 3% | 1 |